



BOUBYAN INTERNATIONAL COMPANY

No:507,5th Floor,

Al-Rihab Complex, Tunis Street,

Hawally, State of Kuwait

Ph. + 91 99424 66663 / + 974 77061 797

Email: ibd@boubyaninternational.com

Website: www.boubyaninternational.com

PRODUCT: POLY ELETOLYTE CATIONIC

SPECIFICATION OF POLY ELECTROLYTES VARIOUS GRADE

POLY ELECTROLYTE – ANIONIC

Anionic Polyelectrolyte has got a wide range of applications right from water purification, oil recovery, color removal, paper making, mineral processing, etc. It has anionic emulsions and dry poly acryl amides which can be used wherever liquid/solids separation is needed in industrial effluent treatment applications.

	STANDARD SPECIFICATION	ACTUAL SPECIFICATION
Degree of Ion(%)	20-30%	25.2%
Molecular Weight	16-20(million)	18.6(million)
PH value	7-10	7.1
Water insoluble matter	≤0.1%	0.08%
Dissolving time	≤60 minutes	52 mint
Density(g/cm3)	≥0.60	0.67
Appearance	Powder	White granular powder

POLYELECTROLYTE (CATIONIC)

Cationic Polyelectrolyte has got a wide range of applications and is mainly used in paper mill and pulp wastewater treatment, or floatation, as well as for thickening and dewatering of sludge (centrifuges, belt filter presses). It can be used in pharmaceutical industries or leather, dyeing and textile for sludge dewatering. The main application is for municipal, slaughter house, sugar, mining and so on for sludge dewatering.

(centrifuges, belt filter presses).

	STANDARD SPECIFICATION	ACTUAL SPECIFICATION
Degree of Ion(%)	15-20%	18.3%
Molecular Weight	6-10(million)	7.8(million)
PH value	3-8	6.3
Water insoluble matter	≤0.1%	0.07%
Dissolving time	≤60 minutes	52 mint
Density(g/cm3)	≥0.60	0.65
Appearance	Powder	White granular powder

POLYELECTROLYTE (NON-IONIC)

Non Ionic Polyelectrolyte is basically water soluble polymers that carry ionic charges. They are organic high molecular weight products with a poly acrylamide base, which are completely soluble in water. It has got a specific application for wide range of industries from water purification, color recovery, etc. in different processes.

	STANDARD SPECIFICATION	ACTUAL SPECIFICATION
Degree of Ion(%)	< 3%	2.79%
Molecular Weight	7-10(million)	7.11(million)
PH value	5-7	6.0
Water insoluble matter	≤0.1%	0.062%
Dissolving time	≤60 minutes	51 mint
Density(g/cm3)	≥0.60	0.62

Appearance	Powder	White
Brookfield Viscosity (cps)	0.1% / 30-50	33

