



BOUBYAN INTERNATIONAL COMPANY

No:507,5th Floor,

Al-Rihab Complex, Tunis Street,

Hawally, State of Kuwait

Ph. + 91 99424 66663 / + 974 77061 797

Email: ibd@boubyaninternational.com

Website: www.boubyaninternational.com

PRODUCT: TALC
PAINT GRADE TALC POWDER

Technical Technical specification on	Paint 60- 10	Paint 60- 20	Paint 60- 38	Paint 58- 15	Paint 57- 63	Paint 35- 45	PTS 6-30	PTS 8-10	PTS 8-63	PTS 8-38
SiO ₂ %≥	60	60	60	58	57	35	35	35	35	35
MgO %≥	31	31	31	30	30	31	28	28	28	28
CaO %≤	0.45	0.45	0.45	0.80	0.80	2.00	2.00	2.00	2.00	2.00
Fe ₂ O ₃ %≤	0.30	0.30	0.30	0.30	0.30	0.30	0.30	0.30	0.30	0.30
Al ₂ O ₃ %≤	0.20	0.20	0.20	0.50	0.50	0.50	6-8	8-10	8-10	8-10
L.O.I. %≤	7.00	7.00	7.00	8.00	9.00	25.00	14.00	14.00	14.00	40.00
D98	50- 55	30- 38	28- 35	40-50	20- 25	20-25	20- 25	40- 50	≥50	≤25

Paint industry

Talc powder
mesh

Whiteness

Remark

Latex paint	325~800mesh	≥ 92.0	
Polyester paint	1250mesh	≥ 94.0	High transparence
Varnish	325-600mesh	≥ 92.0-95.0	High transparence
Auto putty	325-800mesh	≥ 94.0	
Street indicating paint	325-600mesh	≥ 90.0	
Shipping paint	325-800mesh	≥ 92.0-95.0	
Building paint	325-600mesh	≥ 90.0	
Industry paint	325-500esh	≥ 90.0	



BOUBYAN INTERNATIONAL
COMPANY